02-039 (UCT-0064)

## AMENDMENTS TO THE CLAIMS

- 1. (original) A shape memory polymer comprising chemically cross-linked polycyclooctene synthesized from cis-cyclooctene having a high trans double bond content.
- 2. (original) A shape memory polymer according to claim 1 which has been cured by adding dicumyl peroxide to the polycyclocetene.
- 3. (original) A shape memory polymer according to claim 2 further cured through chemical crosslinking upon heating.
- 4. (original) A shape memory polymer according to claim 3 which after curing is cooled to room temperature.
- 5. (amended) A shape memory polymer according to claim 1, having wherein the polycyclocetene has a molecular weight ranging (kg/mol) of from about 120 to about 325 hefore crosslinking.
- 6. (original) A shape memory polymer according to claim 2 having a tunable transition temperature ( $T_m$  of PCO) of about 19 to about 61 °C.
- 7. (original) A shape memory polymer according to claim 2 having a melting point T<sub>m</sub> of about 16 to about 61 °C.
- 8. (original) A shape memory polymer according to claim 2 having a crystallization point T<sub>c</sub> of about 16 to about 39 °C.
- 9. (original) A shape memory polymer according to claim 2 having a melting enthalpy  $\Delta H/J_g^{-1}$  of about 22 to about 63.
- 10. (original) A shape memory polymer according to claim 2 having a melting point  $T_m$  of about 16 to about 61 °C, a crystallization point  $T_c$  of about 16 to about 39 °C and a melting enthalpy  $\Delta H/J_g$  of about 22 to about 63.

02-039 (UCT-0064)

- 11. (original) A shape memory polymer according to claim 2 having a degree of crystallinity at room temperature of from about 2.6% to about 25.5%.
- 12. (original) A shape memory polymer according to claim 2 evidencing rapid shape memory behavior.
- 13. (original) A shape memory polymer according to claim 12 wherein the primary stress-free shape of the polymer is recovered within about 1 second on exposure to temperatures above the melting point of the crystalline polymer phase.
  - 14. (canceled)
- 15. (original) A shape memory polymer molded article formed from a chemically crosslinked polycyclooctene according to claim 1.
  - 16-21. (canceled)
- 22. (original) An impression material for molding, duplication, rapid prototyping, and embossing comprising a shape memory polymer according to claim 2.
- 23. (original) A temperature sensor comprising a shape memory polymer according to claim 2.
- 24. (original) A medical impression material for dentistry, orthopedics and podiatry comprising a shape memory polymer according to claim 2.
  - 25-31. (canceled)
- 32. (new) A shape memory polymer according to claim 1, wherein the polycyclooctene has a trans double bond content of about 68 to about 81%.